

Qual. Nr.	Rohstoff	Garn K / S *	Breite cm	Bin- dung **	Fäden/cm Kette/Schuß	Gewicht g/m ²	Luftdurchl. l/dm ² /min 20 mm WS	Gewebe- dicke micron	Reißkraft N / cm Kette/Schuß	Bemerkung
Qual. No.	Fiber	Yarn Wp / Wt *	Width cm	Weave **	Threads/cm Warp/Weft	Weight g/m ²	Air perm. l/dm ² /min 20 mm HW	Thick- ness micron	Strength N / cm Warp/Weft	Remark

POLYPROPYLEN (E)

2613 PP	mu/fa	104/126	K	28	9	1250	20	2200	4300/1100	
2636 PP	mu/fa	130	L	28	21	740	1	1000	1800/900	kal./cal.
2873 PP	mu/fa	130/160/260	K	64	13	590	20	1000	1500/390	
2876 PP	mu/fa	130/160/250	K	64	13	590	5	900	1500/390	kal./cal.
2646 PP	mo/mu	160	A	118	11	500	5	700	850/1500	kal./cal.
2713 PP	mo/mu	195/270	A	36	9	300	400	640	750/750	
2716 PP	mo/mu	195/250	A	36	9	300	180	560	750/750	kal./cal.
2786 PP	mo/mu	180	A	70	18	410	10	560	900/650	kal./cal.
2816 PP	mo/mu	140/180	A	40	17	290	15	450	960/370	kal./cal.
2696 PP	mo/mo-fa	250/330	K	60	32	450	10	850	750/550	
2676 PP	mo/mo-mu	250/330	K	62	27	480	50	900	800/750	
2656 PP	mo/mo-mo	250/330	K	62	32	430	150	800	800/580	
2666 PP	mo/mo-mo	250/330	K	62	28	460	300	970	800/700	
2623 PP	mo/mo	160	A	118	42	290	80	510	900/350	
2626 PP	mo/mo	160	A	118	42	290	15	420	900/350	kal./cal.
2686 PP	mo/mo	190	K	25	11	260	600	500	700/360	kal./cal.
2685 PP	mo/mo	190	K	25	11	260	1200	550	700/360	kal./cal.
2740 PP	mo/mo	200	L	1,9	1,9	400	-	2200	-	roh/greige
2750 PP	mo/mo	140/160	L	8	6	250	-	850	480/380	roh/greige
2793 PP	mu/mu	130/170	L	3	3	680	-	2000	1250/1250	
2763 PP	mo/mo	195/270	A	36	17	270	1200	550	800/400	
2765 PP	mo/mo	195/250	A	36	17	270	300	450	800/400	kal./cal.
2766 PP	mo/mo	195/250	A	36	17	270	600	500	800/400	kal./cal.
2773 PP	mo/mo	195/270	A	34	16	310	600	650	900/300	
2776 PP	mo/mo	195	A	34	16	310	400	600	900/300	kal./cal.
2866 PP	mo/mo	140	K	42	15	280	200	600	800/300	kal./cal.
2886 PP	mo/mo	180	K	96	21	250	100	450	690/230	kal./cal.

* types of yarn: mo=mono; mu=multi; fa=spun

** types of weave: L=plain; K=twill; A=satin; G=leno

VERSEIDAG TECHFAB

VERSEIDAG-TECHFAB GmbH · Kevelaerer Strasse 78 · D-47608 Geldern – Walbeck
Telefon / Phone: 0 28 31 / 1 22 - 0 · Telefax / Fax: 0 28 31 / 1 22 11, 1 22 35

